

Premium 100%
Acrylic Titanium Base
Weather-Koat 202
Technical Data Sheet

*Exterior Coating & Sealant
Semi-Gloss*

Product Data:

Vehicle: Acrylic Resin

Solvent: Water

Flash Point: None

Drying Time: 1 hour to touch
(77° F & 50% relative humidity)
4 hours to re-coat

Percent Volatile by Volume: 62-64%

Weight by Gallon: 10.65 lbs

Solids - Weight: 49-51%

Solids - Volume: 36-38%

Colors: Standard White
and Custom Colors

Finish: Semi-Gloss

V.O.C.: 1.00 lbs/gal
120 g/L

Environmentally Friendly

Keep Out of Reach of Children

Product Description:

Weather-Koat 202 (Semi-Gloss) Exterior Coating and Sealant is a water-based, highly flexible coating formulated with 100% premium acrylic resins to provide maximum bond strength to resist cracking, checking and delamination. Additional chemical agents are incorporated to resist the effects of ultraviolet sunlight exposure and the growth of mold and fungus in warm and humid climates. This distinctive product has excellent adhesion, outstanding durability and resistance to staining and weathering.

Typical Uses:

Weather-Koat 202 (Semi-Gloss) is engineered and developed to perform under severe industrial, commercial, institutional, agricultural and residential applications. Use on exterior concrete block, pre-cast concrete, masonry, EIFS, hardiboard, wood shake, galvanized, corrugated, and painted metal, aluminum, brick, stone, slate, stucco and wood.

Surface Preparation:

Surface must be dry, clean and free of dirt, grease and mildew. Avoid using cleaners with built-in wax or silicone additives as this may affect coating bond. Remove any trace of mildew by washing with a solution that kills mildew spores. Old coating and/or residue that is loose or peeling must be removed by scraping, sanding, wire brushing or pressure washing. If substrate indicates chalk, a thorough rinse is necessary. If chalking remains, apply *Mastic Primer 101* as a prime coat. Make any necessary repairs or replacements to damaged material. Rusty metal surfaces should be spot primed with *Metal-Koat 102 Rust Inhibitive*. Cracks over ¼" wide should be cleaned and filled with backer rod and/or *Weatherseal SA 27 Caulk*. On new masonry and/or stucco, see *Flex-Koat 204*.

Note: All bare and unpainted finishes may require a primer coat, see *Mastic Primer 101*.

Application:

Maximum adhesion and durability is achieved only when the surface is clean, dry and properly prepared. All surfaces must be uniformly coated and free from voids, pinholes, and blisters. Apply with a brush, roller (¾" – 1½" Nap) or spray equipment (Airless Sprayer – flow output ½ gpm, minimum pressure 2000 psi, tip size .0517. If applying with a roller, maintain a continuous wet edge, with final pass completed in a downward direction. This is to insure a uniform appearance and texture. Drying time is retarded by high humidity. Do not apply at temperatures below 50°F. Coating should have ample time to surface dry before evening dew sets or is rained upon. Apply at approximately one gallon per 200-350 sq. ft.; two coats are recommended for best appearance and durability. Material requirements will increase with coarse or highly weathered surfaces.

Equipment Clean Up: Clean brushes, rollers, spray and other equipment immediately after use with hot soapy water.



2280 Tally Rd, Leesburg, FL 34748
352-728-0777 • Fax: 352-728-6177
www.anchorcoatings.com